ELITE COMPETICIÓN 5W40



AUTOMOTIVE

Lubricants

Description

Designed based on the experience of Repsol's racing teams, this fully synthetic oil can cope with the highest demands to which racing engines are subjected. That is why it is recommended as the best choice for the most advanced and demanding car engines on the market, such as Porsche, Mercedes Benz, Audi, BMW, etc., makes which include it among their most recommended products. A lubricant synonymous with Repsol's success on the race track.

Properties

- The specific additives and synthetic nature of its base oils produce excellent results in high temperature sludge and waste formation tests, ensuring engine cleanliness.
- Recommended by most engine manufacturers for both diesel and petrol vehicles, and with extended oil change periods.
- Engine tests show remarkable resistance to wear, exceeding the minimum requirements, thus enabling longer engine life.
- Its components enable rapid deaeration, thereby minimising the formation of foams at high engine rotation speeds, maintaining lubrication and preventing wear.

Quality levels

- API SN/CF
- ACEA A3/B3, A3/B4
- VW 502.00/505.00
- MB 229.3
- BMW LL-01
- PORSCHE A40
- RN0700, RN0710
- GM LL-B-025

Technical specifications

| | UNIT | METHOD | VALUE |
|--|----------|-------------|------------|
| SAE GRADE | | | 5W40 |
| Density at 15 °C | g/mL | ASTM D 4052 | 0.850 |
| Viscosity at 100 °C | cSt | ASTM D 445 | 14.1 |
| Viscosity at 40 °C | cSt | ASTM D 445 | 87 |
| Viscosity at -30 °C | сР | ASTM D 5293 | 6600 max. |
| Viscosity index | - | ASTM D 2270 | 170 |
| Flash point, open cup | °C | ASTM D 92 | 215 min. |
| Pour point | °C | ASTM D 97 | -36 |
| T.B.N. | mg KOH/g | ASTM D 2896 | 10.5 |
| Sulphated ash | % weight | ASTM D 874 | 1.5 max. |
| Bosch Injector Shearing: Viscosity at 100 °C after shearing | cSt | CEC-L-14-93 | 12.5 min. |
| Noack volatility, 1hr at 250 °C | cSt | CEC-L-40-93 | 11.5% max. |

A safety data sheet is available on request.

repsol.com +34 901 111 999

Technical data sheet for Lubricants. Revision 7. September 2011.